

(19)



JAPANESE PATENT OFFICE

PATENT ABSTRACTS OF JAPAN

(11) Publication number: **10323828 A**

(43) Date of publication of application: **08.12.98**

(51) Int. Cl.

B29B 9/06

B29C 47/40

(21) Application number: **09135179**

(22) Date of filing: **26.05.97**

(71) Applicant: **JAPAN STEEL WORKS LTD:THE**

(72) Inventor:
HANDA KIYOSHI
KUBOTA KANSABURO
ODA NORIKIYO

(54) **METHOD AND APPARATUS FOR
MANUFACTURING THERMOPLASTIC RESIN
PELLET**

disposed via a small interstice G of about 1 mm to 2 mm
from the tip of the screws 3, 4:

COPYRIGHT: (C)1998,JPO

(57) Abstract:

PROBLEM TO BE SOLVED: To pelletize material extruded from a kneading machine directly by performing extrusion in a state of the tip end of a screw of a biaxial kneading extruder put in the proximity of the inner surface of dies in a manufacturing method of pellets by melt kneading resin material with a biaxial kneading extruder, and extruding molten material from dies to be granulated subsequently.

SOLUTION: A granulating machine 6 comprising dies 5 and a cutter unit is connection secured at the tip of a biaxial kneading extruder 1. The dies 5 is substantially in the shape of a disk, and on the back surface thereof, two conical recesses 5a are formed adjoining in conformation with the distal end configurations of screws 3, 4, followed by forming a plurality of dies holes that pierce in the direction of thickness. In addition, the dies 5 has a flow path for temperature control fluid formed penetrating in the board face direction around the dies holes. The flow path is connected with a temperature control fluid pipe. The dies 5 is made such that the back face recesses 5a are

